arXiv:1302.0659v2 [cond-mat.mes-hall] 7 Feb 2013

Robust synchronization of an arbitrary number of spin-torque driven vortex nanooscillators

Sergey Erokhin and Dmitry Berkov*
Innovent Technology Development, Prüssingstraße 27B, D-07745, Jena, Germany
(Dated: February 8, 2013)

Non-linear magnetization dynamics in ferromagnetic nanoelements excited by the spin-polarized dc-current is one of the most intensively studied phenomena in solid state magnetism. Despite immense efforts, synchronization of oscillations induced in several such nanoelements (spin-torque driven nanooscillators, or STNO) still represents a major challenge both from the fundamental and technological point of view. Here we propose a system where synchronization of any number of STNOs in a wide current range can be easily achieved, and the inclusion of thermal fluctuations does not disturb it. Our STNOs are represented by vortices inside squared nanoelements, which precession is driven by current injected via point contacts. Using full-scale micromagnetic simulations we show that synchronization of these STNOs is extremely dynamically stable due to a very large coupling energy provided by the magnetodipolar and exchange interaction between nanoelements. Finally, using as an example a system of 10 oscillators, we demonstrate that our concept allows robust synchronization of arbitrary number of STNOs, even when corresponding nanocontacts have a broad size distribution.

Magnetization excitation and switching in thin ferromagnetic films and nanoelements induced by the injection of a spin-polarized dc-current is a very active research area of modern solid state physics due to the large importance of these phenomena for our fundamental understanding of electrical and magnetic properties of condensed matter [1–3]. Particularly, an enormous attention has been paid to excitations of a special type - steady state gyration of magnetic vortices governed by the spin-polarization of injected current. This object is a highly non-trivial example of a nanosized oscillator with strongly nonlinear properties. For this reason the study of its dynamical behavior, which should lead to the decisive improvement of our general understanding of interaction effects in such systems, is one of the most important tasks of the current research in non-linear magnetic phenomena. Especially various synchronization regimes in ensembles of these oscillators represent a very challenging fundamental problem, which solution for various cases has been the subject of many recent publications [4–9].

This interest is strongly supported by many promising applications of this novel effect [10, 11]. Among these applications, one of the most important would be a nanosized microwave signal generator which frequency could be tuned by changing either the external magnetic field or the dc-current strength. Such generator could be very useful in, e.g., detectors of microwave fields and telecommunication appliances.

Despite large experimental and theoretical efforts aimed to create such generators, the power and linewidth of a single spin torque-driven nanooscillator (STNO) are still not competitive with corresponding non-magnetic state-of-the-art devices. Decisive improvement of STNO-based generators is expected from synchronization (phase-locking) of several STNOs, what would result both in a quadratic increase of the output power ($\sim N^2$ for N synchronized oscillators) and substantial narrowing of the generated linewidth. Unfortunately, although intensive theoretical research led a substantial deepening of our understanding of synchronization process of two and more STNOs [4–9, 12, 13], experimental achievements here remain rather modest: in pioneering reports [14, 15] two closely placed point contact STNOs could be synchronized, and afterwards only in one experimental paper [16] the synchronization of four such oscillators was demonstrated.

In most theoretical and experimental studies synchronization of STNOs with the nearly collinear magnetization configuration under the contact is considered. Recently it has been shown that the steady-state gyration of a magnetic vortex [17, 18] is also a possible candidate for realizing a system of synchronized STNOs [9, 16, 19].

In this study we present the system design which allows the robust synchronization of an *arbitrary* number of vortex-based STNOs in a wide range of current strengths, even when the diameters of corresponding point contacts are significantly different. The proposed system exhibits a very high coupling energy between the constituent STNOs. For this reason the synchronization is stable with respect to thermal fluctuations, as we have also verified by corresponding simulations.

To provide a basis for the understanding of our many-vortices system, we start with the brief description of the magnetization dynamics of a single vortex-based STNO. The vortex nanooscillator used in this study is based on the square-shaped nanoelement with lateral sizes 500×500 nm^2 and thickness $h = 20$ nm; this thickness corresponds to a typical experimental system (see, e.g., [19]). The current with the out-of-plane spin polarization direction and polarization degree $P = 0.3$ is injected via the point contact with the diameter $D = 100$ nm (unless stated otherwise, see last section) in the center of the nanosquare. Magnetic parameters typical for Permalloy are chosen: magnetization $M_S = 860$ G, exchange constant $A = 1.0 \times 10^{-6}$ erg/cm, negligibly small crystallographic magnetic anisotropy and Gilbert damping $\lambda = 0.01$. To prevent the reversal of the core polarity for high current values (see below for details), the constant external field $H_{\mathrm{perp}} = 2$ kOe was applied perpendicularly to the nanoelement plane. This sample and all other systems studied below were discretized only in-plane using a 4×4 nm^2 mesh. Micromagnetic determination of the equilibrium system state and dynamic simulations of the spin torque-induced magnetization dynamics were carried out with our MicroMa-



FIG. 1. (color online) Magnetization dynamics of a single STNO: (a) and (b) - snapshots of typical magnetization configurations in low- and high-current oscillation regimes (red solid circles define the nanocontact area, the green dotted line in (a) is the vortex trajectory); (c) spectral amplitude of magnetization oscillations under the contact.

gus software package [20], which dynamical part solves the Landau-Lifshitz-Gilbert equation of motion for magnetic moments including the additional term for the spin-torque.

For all systems studied in this article below magnetization dynamics was simulated during 200 ns of the 'physical time', starting from the time moment when the current was switched on. In order to explore only the steady precession regime, all spectra presented below have been calculated from the data collected for 100 ns $< t <$ 200 ns.

The next important issue is how to initiate the vortex gyration, because without the external in-plane field and due the presence of the circularly symmetric Oersted field, the vortex core position in the center of the nanocontact corresponds to the state with the minimal magnetic free energy. To induce the vortex oscillations, an in-plane field pulse with the amplitude 200 Oe and duration 3 ns was applied. This pulse was strong enough to 'knock out' the vortex core from the nanocontact center to the region outside the contact. In this region the competing influences of the spin torque, Gilbert damping, Oersted field and the stray field from the borders of the nanosquare led to the core motion around the point contact. After the system 'forgets' the initial in-plane field pulse, this rotation occurs by a nearly circular orbit.

Simulation results for the single nanooscillator described above are shown in Fig. 1(c). Note, that on this and all other figures we display the spectral amplitude of oscillations of the in-plane (m_x) magnetization component under the point contact(s), thus simulating the effect measured by GMR. Simulations performed in the current interval $0.5 < I < 10$ mA reveal that there exist two dynamical regimes: 'simple' vortex rotation around the nanocontact (for $I < 8$ mA) and the



FIG. 2. (color online) Magnetization dynamics of two dipolar-coupled STNOs: (a) - snapshot of a typical magnetization configuration in a synchronized regime (note opposite oscillation phases under the two contacts); (b) time dependencies of the average magnetization under the 1st ($m^x_1(t)$, red line) and 2nd ($m^x_2(t)$, blue line) contacts and the their sum ($m^x_{\rm tot}(t)$, green line); (c) - spectral amplitude of the sum of magnetizations under the contacts $m^x_{\rm tot}(t) = m^x_1(t) + m^x_2(t)$; (d) total oscillation power of the *difference* $m^x_{\rm diff}(t) = m^x_1(t) - m^x_2(t)$, demonstrating the large power increase in the synchronized regime if the additional phase shift of π is introduced between the ac-currents generated by the two contacts.

regime, where the rotating vortex generates vortex-antivortex (V-AV) pairs ($I > 8$ mA). In the latter case, the V-AV pair annihilates very quickly again [21], leading to the emission of a spin-wave burst, which is the dominating mechanism of the energy dissipation in the high-current regime. For the spin torque-induced vortex dynamics, this process has been discussed in detail for a somewhat different point-contact system in [19], so that we do not elaborate this issue further. We only note, that in our case there is no core polarity switching due to the out-of-plane external field, so that the remaining vortex simply increases its angular velocity again until the next V-AV



FIG. 3. (color online) Magnetization dynamics of the two STNOs connected by a 'bridge' (partial exchange coupling), shown in same way as in Fig. 2(c). STNOs are synchronized almost in the whole current region, where their steady-state gyration is observed.



FIG. 4. (color online) Magnetization dynamics of the two STNOs with a full exchange coupling, presented in same way as in Fig. 2(c). Vortex gyration is out-of-phase almost for current values, leading to in-phase magnetization oscillations under the contacts.

pair is generated. We present a snap-shot of the m_x-component for the first regime in Fig. 1(a) (white corresponds to $m_x = +1$ and black - to $m_x = -1$) and a snap-shot of the out-of-plane m-component immediately after the annihilation of the V-AV pair for the second regime - in Fig. 1(b); in this last image, diverging spin waves generated by the V-AV annihilation can be clearly seen.

Now we can proceed with the analysis of synchronization in a systems of two nanooscillators. For the synchronization of STNOs, the first (low-current) regime is obviously more suitable. We point out, that in this regime for our system the vortex rotation frequency depends on the current strength very weakly already for small currents and is nearly constant for currents above ≈ 4 mA (see Fig. 1(c)). This behavior is in a strong contrast with the results reported previously for the in-plane magnetized nanocontacts [14, 15] and also differs considerably from the $f(I)$-dependence found in [17, 19]. Detailed discussion of possible reasons for this difference will be presented elsewhere. Here we would like only to emphasize that such a weak dependence $f(I)$ is a good prerequisite for the synchronization of STNOs in a broad current range.

In this study, we investigate three kinds of coupled STNO systems, where the oscillators are coupled in different ways: (i) dipolar coupling only, i.e., nanosquares (placed in one plane) are fully separated by a narrow gap having the width $d = 48$ nm, see Fig. 2(a); (ii) dipolar and partial exchange coupling, i.e., nanosquares are partially connected by the bridge with the same thickness $h = 20$ nm and the width $l = 200$ nm, made of the same magnetic material (Fig. 3(a)); and (iii) dipolar and full exchange coupling, realized as a system of two STNOs fully connected along their sides (Fig. 4(a)). In contrast to circular vortex-based STNOs used, e.g., in [9], we have chosen the square-shaped nanoelements, because in this case the dipolar coupling caused by surface magnetic charges on closely placed parallel edges of two such nanoelements should be much stronger than the corresponding coupling of two circular elements (we note in passing that the patterning of square-shaped nanoelements should be also more convenient from the technological point of view). For all three systems we have studied their dynamic behavior for currents through the 1st nanocontact in the region $0.5 < I_1 < 10$ mA, whereby the second current strength was kept constant ($I_2 = 5$ mA). Simulations for each value of I_1 were performed independently.

The choice of the current and spin polarization directions for the two contacts system requires a special discussion. The current direction defines the rotation sense of its Oersted field and thus - the rotation sense of the equilibrium Landau domain pattern in each nanosquare. The latter, in turn, defines the chirality of the corresponding vortex (polarities of all vortices are identical due to the presence of the out-of-plane external field). If the current directions are the same for both



FIG. 5. (color online) Coupling energy vs current strength for systems of two vortex STNOs: triangles - system with dipolar coupling only (Fig. 2(1)), squares - 'bridge' configuration (Fig. 3(a)), circles - full exchange and dipolar coupling (Fig. 4(a)).

contacts, then the sign of the out-of-plane spin polarization projections P_{perp} is also the same (we remind, in a real system the sign of P_{perp} is determined by the current direction and the sign of the out-of-plane magnetization component of the 'hard' magnetic underlayer). In this situation the gyration sense of both vortices coincide, providing favorable conditions for the STNOs synchronization. However, if the rotation senses of equilibrium domain patterns are the same in both nanosquares, an antivortex is formed between the vortices in exchange-coupled systems (cases (ii) and (iii) listed above). Such an antivortex is a strong undesired perturbing factor, because its dynamics can not be satisfactorily controlled by external parameters even in the regime where no additional V-AV pairs are generated: the antivortex annihilates unavoidably with one of the oscillating vortices (after the V-AV distance reaches some minimal value), thus destroying one of STNOs. For these reasons we propose to use currents having *opposite* directions for adjacent point contacts, so that the rotation senses of the vortices created by corresponding Oersted fields are also opposite; for this configuration no antivortex is formed in exchange-coupled systems. In this case the spin polarization directions would also be opposite, so that the gyration senses of adjacent vortices remain the same.

Results for the case (i) of dipolar-coupled nanoelements are summarized in Fig. 2. For the current directions and spin polarizations used here, in the steady precession regime both vortices rotate clockwise around the contacts. After the initial in-plane field pulse expels the vortices out of contact areas, the magnetization within these areas rotates 'in-phase' for several tens of nanoseconds, but afterwards a transition to an 'out-of-phase' rotation occurs, as shown in Fig. 2(b). Details of this highly interesting transient dynamics governed by interaction between vortices will be discussed elsewhere.

From the oscillation power spectra of the sum $m^x_{\text{tot}}(t) = m^x_1(t) + m^x_2(t)$ of magnetization components under the 1st and 2nd contacts shown in Fig. 2(c), it is clear that the synchronization of two STNOs occurs nearly in the entire current interval of the regular vortex precession (i.e., where no V-AV pairs are generated) $1.5 < I_1 < 7$ mA. In this interval, the total power at the fundamental frequency $f = 0.50$ GHz nearly disappears (for $3 < I_1 < 6.5$ mA it is below 10^{-6} of the power for a single STNO), thus signaling the perfect out-of-phase synchronization of two oscillators. Indeed, the snap-shot in Fig. 2(a) shows that the vortex cores precess in-phase, but due to their opposite chiralities, magnetic moments under the contacts rotate out-of-phase, so that their sum m^x_{tot} is approximately zero.

In an experimental system, in order to obtain the maximal output power, one would either perform the phase shift of one of the currents by π, or use the underlayers with the opposite orientations of the in-plane magnetization projections; in both approaches the GMR signals from the two contacts would become in-phase. In this case one would obtain the dependence of the total oscillation power on the current strength $P(I_1)$ shown in Fig. 2(d), where we have plotted the total oscillation power of $m^x_{\text{diff}}(t) = m^x_1(t) + m^x_2(t) \cdot \exp(i\pi) = m^x_1(t) - m^x_2(t)$. As it should be, we observe a strong enhancement of P in the synchronized regime. This enhancement is even somewhat more than two times (the maximal increase expected for two ideal synchronized oscillators), because for low and high currents, where the oscillators are not synchronized, the magnetization under contacts is not entirely coherent.

For the second system, where the nanosquares are connected via a bridge, vortex STNOs interact both via the dipolar and exchange interaction. We remind, that due to the chosen current directions we avoid the formation of the antivortex between the vortices, so that the we still can obtain a stable steady-state precession of vortices and their synchronization, as shown in Fig. 3(a). Due to the presence of an additional exchange coupling, synchronization starts to establish itself already for the smallest current where the vortex precession could be induced (see Fig. 3, (b) and (c)). As in the previous case, magnetization oscillations under the contacts in the synchronized regime are out of-phase.

The third system - fully connected square-shaped nanoelements (so that they form a single rectangle) - demonstrates a qualitatively different type of synchronization (Fig. 4(a): the strong exchange interaction between STNOs leads mostly to out-of-phase vortex core oscillations (and the vortex trajectories are strongly non-circular), so that magnetization oscillations under the contacts are *in-phase*. However, the synchronized state observed on previous systems - with the in-phase vortex oscillations and out-of-phase m_x-oscillations under the contacts - is also possible, as it can be seen from the spectral power 'gaps' around $I_1 = 3.5$ mA and 6.5 mA in Fig. 4(b). The existence of such multiply synchronized states has been reported for another system of synchronized STNOs [22]. We also point out that for large currents, where in previous systems the V-AV pairs were generated, we still observe here synchronization, but with several frequency jumps (Fig. 4(b)); corresponding processes will be discussed in details



FIG. 6. Snapshots of the in-plane magnetization distributions for 10 nanooscillators in the transient (t = 15 ns, upper panel) and synchronized (t = 116 ns, lower panel) regimes.



FIG. 7. Total oscillation power (normalized to the oscillation power of one STNO) of the alternating sum of the in-plane components inside the point contacts $m^x_{\rm alt}(t) = \sum_i (-1)^{i-1} m^x_i(t)$, which takes into account the opposite oscillation phases of the magnetization in adjacent contacts.

elsewhere.

One of the most important parameters of a synchronized system is the coupling energy between the oscillators $E_{\rm coup}$. This quantity defines not only the current range where synchronization occurs and the maximal allowed frequency mismatch between single oscillators [4, 6, 9], but also the stability of the synchronization against thermal fluctuations. For some simple cases there exist analytical and semianalytical methods for the estimation of $E_{\rm coup}$ [4, 9], but for complex systems like dipolar- and exchange-coupled vortices reliable analytical methods to compute this quantity are lacking.

For this reason we suggest here a purely numerical and generally applicable method for calculation of the coupling energy. First we note, that the total energy of the synchronized system even in a steady-state oscillation regime is not constant, but oscillates slightly in time: $E_{\rm tot} = E_{\rm tot}(t)$. Averaging $E_{\rm tot}(t)$ over at least one oscillation period (better over several periods), we obtain the *averaged* total system energy $\langle E_{\rm tot} \rangle$. Subtracting from this quantity the equilibrium system energy $E_{\rm eq}$ at $T = 0$ (where the Oersted field is already present, but the spin-transfer torque is still switched off), we obtain the dynamical contribution to the total energy $E^{\rm dyn}_{\rm sync}$, pumped into the system by the spin-transfer torque: $E^{\rm dyn}_{\rm sync} = \langle E_{\rm tot} \rangle - E_{\rm eq}$. Then we repeat this procedure for each oscillator independently, obtaining the dynamical additives $E^{\rm dyn}_1$ and $E^{\rm dyn}_1$ for the oscillators 1 and 2 operating separately; all these energies depend, of course, on the current strength. The difference between the dynamical additive for the system of vortices in the synchronized regime $E^{\rm dyn}_{\rm sync}$ and the sum of $E^{\rm dyn}$ of two STNOs separately (operating at the same current strengths as the synchronized system) provides a dynamical coupling energy: $E_{\rm coup} = E^{\rm dyn}_{\rm sync} - (E^{\rm dyn}_1 + E^{\rm dyn}_2)$.

Results of this calculation for all three systems studied above are presented in Fig. 5, where the plots of the absolute values of $E_{\rm coup}$ (which are by itself obviously negative) are shown; note the logarithmic scale of the energy axis. The numbers on the plot are the coupling energies for I_1 = 5 mA (I_2 = 5 mA, as always). First we note, that even for the system with only the dipolar interaction between STNOs the coupling energy is roughly twenty times larger than kT. For this reason we expect the effect of thermal fluctuations in these systems to be irrelevant. We have verified this expectation by micromagnetic modeling including thermal fluctuations at T = 300 K. The spectral amplitude map $P(f, I_1)$ for this temperature was very similar to that presented in Fig. 2(c) for $T = 0$. Comparison of the total powers for $T = 0$ and T = 300 K (Fig. 2(d)) demonstrates that thermal fluctuations do not really affect the synchronization dynamics even for this system with the weakest coupling between STNOs. We also note, that the coupling energy $E_{\rm coup} = 8.4 \times 10^{-13}$ for this our system is roughly four times larger than $E_{\rm coup} = 2.3 \times 10^{-13}$ erg, calculated in [9] for two vortex-based STNOs with the circular shape; this difference, however, should be attributed partially to the larger thickness of our nanoelements.

For the fully exchange-coupled system the relation of typical coupling energy to the thermal energy is $E_{\rm coup}/kT \approx 2.9 \times 10^{-11}/4.1 \times 10^{-14} \approx 700$ (Fig. 5), so that in this system thermal fluctuations should play no role whatsoever.

The last very important point is that our design allows the synchronization of an arbitrary number of vortex-based STNOs, arranged, e.g., as a regular chain. To demonstrate this fact, we have performed simulations of a system consisting of 10 dipolarly coupled oscillators placed as shown in Fig. 6; the total system size is 5430×500 nm^2. Here, *total* currents (not the current densities) flowing through all contacts have been taken to be equal; the value of this current was varied from 0.5 to 7 mA.

In these simulations, we have addressed another very important problem: how stable is the synchronization with respect to random fluctuations of the point contact diameters, unavoidable in technological processes used for manufacturing of such contacts. Simulating a single STNO, we have found that the vortex gyration frequency is nearly independent on the point contact diameter, if the total current through the contact is kept constant. The reason is, that the vortex oscillation orbit lies outside the point contact region, where the Oersted field (and thus - the vortex dynamics) depends only on *total* current flowing through the contact. Hence a robust synchronization of many STNOs based on point contacts with very different diameters can be expected, as long as the currents strengths (which can be controlled experimentally very precisely) through all contacts are the same. In our simulations we have used a system of 10 STNOs, with contacts diameters having a normal distribution with the mean $\bar{D} = 90$ nm and dispersion $\sigma = 30$ nm; in our concrete system realization the contacts have the diameters $60 < D < 120$ nm. Fig. 6 displays in-plane magnetization distributions for two time moments: a few nanoseconds after the external field pulse has been switched off ($t = 15$ ns) and 100 ns later, when oscillators are almost perfectly synchronized. Plot of the total oscillation power (normalized to the oscillation power of one STNO) vs current (Fig. 7) shows that a huge power gain of nearly 100 times (close to a maximal theoretical value) can be obtained in this highly non-ideal system for currents $I_0 > 4$ mA.

In summary, we predict, that in various kinds of systems consisting of several vortex-based STNOs driven by a spin-polarized current which flows through point contacts attached to square-shaped magnetic nanoelements, a highly stable synchronization of these nanooscillators can be achieved. Using a general method to calculate the coupling energy $E_{\rm coup}$ of synchronized STNOs suggested by us, we show that in such a system $E_{\rm coup}$ can be up to three orders of magnitude higher than kT, so that the influence of thermal fluctuations is expected to be fully negligible. Finally, we demonstrate, that a robust synchronization of an *arbitrary* number of spin-torque driven vortex nanooscillators can be easily obtained using our suggested system setup. This synchronization remains stable also in a system where a significant (experimentally unavoidable) distribution of the point contact diameters is present.

---

[*] db@innovent-jena.de

[1] J. Slonczewsky, *Handbook of Magnetism and Advanced Magnetic Materials*, edited by H. Kronmüller and S. Parkin, Vol. 5: Spintronics and Magnetoelectronics (John Wiley & Sons, 2007).

[2] M. Stiles, *Handbook of Magnetism and Advanced Magnetic Materials*, edited by H. Kronmüller and S. Parkin, Vol. 5: Spintronics and Magnetoelectronics (John Wiley & Sons, 2007).

[3] D. Ralph and M. Stiles, J. Magn. Magn. Mater. **320**, 1190 (2008).

[4] A. N. Slavin and V. S. Tiberkevich, Phys. Rev. B **74**, 104401 (2006).

[5] V. Tiberkevich, A. Slavin, E. Bankowski, and G. Gerhart, Applied Physics Letters **95**, 262505 (2009).

[6] X. Chen and R. H. Victora, Phys. Rev. B **79**, 180402 (2009).

[7] D. Li, Y. Zhou, C. Zhou, and B. Hu, Phys. Rev. B **82**, 140407 (2010).

[8] D. Li, Y. Zhou, B. Hu, and C. Zhou, Phys. Rev. B **84**, 104414 (2011).

[9] A. D. Belanovsky, N. Locatelli, P. N. Skirdkov, F. A. Araujo, J. Grollier, K. A. Zvezdin, V. Cros, and A. K. Zvezdin, Phys. Rev. B **85**, 100409 (2012).

[10] T. Silva and W. Rippard, J. Magn. Magn. Mater. **320**, 1260 (2008).

[11] J. Katine and E. Fullerton, J. Magn. Magn. Mater. **320**, 1217 (2008).

[12] A. N. Slavin and V. S. Tiberkevich, Phys. Rev. B **72**, 092407 (2005).

[13] S. M. Rezende, F. M. de Aguiar, R. L. Rodriguez-Suarez, and A. Azevedo, Phys. Rev. Lett. **98**, 087202 (2007).

[14] S. Kaka, M. R. Pufall, W. H. Rippard, T. J. Silva, S. E. Russek, and J. a. Katine, Nature **437**, 389 (2005).

[15] F. B. Mancoff, N. D. Rizzo, B. N. Engel, and S. Tehrani, Nature **437**, 393 (2005).

[16] A. Ruotolo, V. Cros, and B. Georges, Nature Nanotechnology **4**, 528 (2009).

[17] Q. Mistral, M. van Kampen, G. Hrkac, J.-V. Kim, T. Devolder, P. Crozat, C. Chappert, L. Lagae, and T. Schrefl, Phys. Rev. Lett. **100**, 257201 (2008).

[18] M. Darques, A. Dussaux, A. V. Khvalkovskiy, J. De la Torre Medina, F. Abreu Araujo, R. Guillemet, K. Bouzehouane, S. Fusil, J. Grollier, G. G. Avanesyan, K. A. Zvezdin, V. Cros, and L. Piraux, Journal of Physics D: Applied Physics **44**, 105003 (2011).

[19] S. Petit-Watelot, J.-V. Kim, A. Ruotolo, R. M. Otxoa, K. Bouzehouane, J. Grollier, A. Vansteenkiste, B. Van de Wiele, V. Cros, and T. Devolder, Nature Physics **8**, 682 (2012).

[20] D. V. Berkov and N. L. Gorn, "Micromagus: package for micromagnetic simulations," .

[21] R. Hertel and C. M. Schneider, Phys. Rev. Lett. **97**, 177202 (2006).

[22] D. V. Berkov, Phys. Rev. B **87**, 014406 (2013).